

CEL-SPAN®

Process Aid 333



PHOENIX
Plastics™
www.phoenixplastics.com

Cel-Span® Process Aid 333

A clear compounded product that protects film resin during high temperature processing.

Cel-Span® Process Aid 333 is a compounded product intended for clear films containing a high level of thermal stabilizers to provide protection of film resins during high temperature extrusion and lamination processes, thus maximizing inherent the natural resins. Cel-Span® Process Aid 333 eliminates build up in both internal and external metal surfaces of the extrusion die, as well as reduction of wrinkles in thin gauge films.

Applications: Film

Melt-flow: 1.0 dg /10min.

Blend Density: 0.918 g/cc

Pellet Size: 1/8" round pellet

Color: Beige/Natural

Pellet/Gram: 35/45

Features and Benefits:

Cel-Span® Process Aid 333 is an effective masterbatch for polyolefins especially HDPE, LDPE and LLPDE used to enhance physical properties of the natural resin like puncture resistance, tear propagation, and anti-blocking properties coupled with excellent thermal stabilization and reduction of wrinkles. Cel-Span® Process Aid 333 is also recommended to heat stabilize and reduce die build up of lamination films exceeding 600°F and above. The product is used at a 3%-5% level in LDPE or LLDPE film resins to reduce or eliminate die lines and build up on internal and external die metal surfaces Cel-Span® Process Aid 333 additives are listed on the TASCAs list. There are no adverse health effects from the use of Cel-Span® Process Aid 333. Cel-Span® Process Aid 333 is packaged in 55 lb. plastic bags or 1,100 lb. gaylord boxes. We recommend this product be kept closed and stored in the original container, away from light, heat, and highly humid environments.

Disclaimer - This data contains general information and describes typical properties only. Only persons qualified to determine for themselves the suitability of our products for particular purposes should evaluate its potential uses. No guarantee is made or liability assumed, the application of this data and the products describes herein being at the sole risk of the user. Samples are provided to the requester on an "AS IS, WHERE IS" evaluation purpose only basis, solely under the use and direction of the requester, without warranty of any kind (either express or implied), including but not limited to any implied warranties of merchantability and fitness for a specific or general purpose and those arising by statute or by law, or from a cause of dealing or usage of trade. In no event, regardless of cause, shall Phoenix Plastics be liable for any indirect, special, incidental, punitive or consequential damages of any kind, whether arising under breach of contract, tort (including negligence), strict liability or otherwise, and whether based on this agreement or otherwise, even if advised of the possibility of such damages.